

安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

安徽省蚌埠市高新区兴中路 985 号

日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

TDS of Side Chain Type Vinyl silicone oil IOTA 272

Structural Formula

Description

- 1. Vinyl silicone oil (Side-chain type) is the middle of the molecular chain with methyl vinyl polysiloxane.
- 2. The molecular weight and vinyl content of the product free configuration.
- 3. This product have the methyl silicone oil's common performance (such as: smoothness, limpness, bright, temperature and durability etc.
- 4. Molecular chain has a good reactivity.can participate in a variety of chemical reactions, such as: addition reaction, free radical reactions etc.
- 5. For containing vinyl, therefore, this product compared with silicone oil, and some material has better intermiscibility.

Specification

Test	Unit	Value
Appearance		colorless light yellow liquid
Viscosity	25°C, MPas	250-500、1000-1500、2500-3000
Vinyl content	%	2-3, 0.5-0.8
PH		6-8



安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

安徽省蚌埠市高新区兴中路 985 号 日月科技园

电话: 86-552-3827158 传真: 86-552-3822922

Application

- 1. As macromolecules, high viscosity110-2 silicone rubber's hardening agent and diluent before vulcanization..
- 2. As some organic materials modifier, such as acryl resin, ethylene vinylacetate copolymer resin.
- 3.For making high-temperature vulcanized silicone rubber, and medium temperature vulcanized silicone rubber and silicone gel.

Usage And Dosage

When used as thinner the quantity of 10%-20%, when used as a modifier to add the quantity of 5%-10%, when used as silicone rubber the quantity of 50%-100%. direct into the high-speed mixing or strong mixing or stirring devices into the system in order to ensure uniform dispersion.

Package and Transportation

- 1. This product should be stored airtight at room temperature in dry shade, not near the fire source, avoid sun exposure, avoid mixing of impurities (especially catalysts, acid substances), by non-dangerous goods storage and transportation.
- 2. Packed with 200KG and 50KG polyethylene plastic barrel

Note

This material have chemistry's lively, should not to mixed with impurities (especially the catalyst), when in use or compatibility of medicines, should be notice if have chemical reaction, prevent degeneration.

For details, please contact,

IOTA CORPORATION LTD.



安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

安徽省蚌埠市高新区兴中路 985 号

日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Mobile/Wechat: 0086-15255260163

QQ: 3374697933

Email: info@htvsilicone.com

Website: www.htvsilicone.com