

安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

安徽省蚌埠市高新区兴中路 985 号 日月科技园

电话: 86-552-3827158 传真: 86-552-3822922

TDS of RTV Phenyl Silicone Gum IOTA 35

Phenyl Silicone gum (RTV; Dihydroxy Poly Dimethyl Diphenyl Siloxane

Molecular Formula: (CH₃)₂SiOH[(C₆H₅)₂SiO]_m[(CH₃)₂SiO]_nOH

Structure:

Specifications:

Appearance	Colorless or yellowish transparent liquid
Phenyl Content (mol %)	2.5-20.0
Viscosity 25°C mPa.s	2000-10000
Volatile (150°C/2h) ≤	3.0
Solubility	Soluble in organic solvent such as toluene,
	xylene, chlorinated hydrocarbons

Application:

This product in addition to the excellent electrical properties, corrosion resistance, ozone resistance, also has good resistance to low temperature performance of irradiation, self-extinguishing and ablation resistance. Can be used for a variety of original electronic potting materials, and materials for dipping impression and stripping, a component of binder. At minus 120 °C under the condition of low temperature remains resilient, available for special purposes.

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.personalcaresilicone.com



安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

安徽省蚌埠市高新区兴中路 985 号 日月科技园

电话: 86-552-3827158 传真: 86-552-3822922

Package:

N. W. 25KGS/Plastic drum, transported and stored as non-dangerous goods, avoid sun and rain exposure, isolated from fire, away from heat source. Over the storage period 3 years should review, if qualified can use.

For details, please contact,

IOTA CORPORATION LTD.

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Mobile/Wechat: 0086-15255260163

QQ: 3374697933

Email: info@htvsilicone.com

Website: www.htvsilicone.com